

UPM Raflatac Technical Information

21.04.2017 ENG 4041

Product	POLYLASER GLOSS CLEAR / RPAF / KRAFT SP STABILIZED 120		
Sales Code	M7/RPAF/FGX		
EAN	6415788238134		
Product use	Product designed for laser printed gloss clear logistics and industrial variable information label applications. It can be also used in address labelling or other information labelling in SOHO end-uses. This filmic product has excellent tolerance for temperature and humidity fluctuations.		
Face	POLYLASER GLOSS CLEAR		
Product	Transparent, gloss coated heat stabilized polyester film.		
Substance	71	g/m ²	DIN 53352
Caliper	50	µm	DIN 53370
Elongation MD	155.0	%	DIN 53455
Elongation CD	110.0	%	DIN 53455
Printability	Suitable for laser and common label printing methods like flexography, screen and offset due to the pre-treatment. Special inks designed for non-absorbent materials should be used. Depending on printer used, especially in low humidity conditions, static electricity might occur. To reduce this effect store your media in temperature and humidity controlled conditions. In critical cases manual feed or bypass tray is recommended. Fan the pile of sheets prior printing in order to release accumulated electric charge.		
Shelf life	Laminate with RP37, RPAF, RR28 and RRAF adhesives 2 years if stored at room temperature (+20 °C), RH 50% in original packaging and protected from light.		
Adhesive	RPAF		
Type	General purpose permanent adhesive for A4 and cut-size applications.		
Composition	Acrylic, water borne.		
Tack min	9	N/25mm	FTM 9
Backing	KRAFT SPECIAL STABILIZED 120		
Product	White woodfree kraft backing paper.		
Substance	120	g/m ²	ISO 536
Caliper	112	µm	ISO 534
Tensile strength MD	8.0	kN/m	ISO 1924
Tensile strength CD	4.0	kN/m	ISO 1924
Advantages	High dimensional stability providing superior lay-flatness. Specially developed for SOHO, medium and high volume laser printers		
Performance			
Minimum labelling temperature	5 °C		
Service temperature	-20 °C to 100 °C		


UPM

Shelf life From the date of manufacture: 2 years at +20 °C and RH 50%. Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Limitations Limited adhesion at low temperatures. The highest end-use temperature must be separately checked together with the face material.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.



UPM